

Kunlun™1070D
technical data sheet



*This product model has undergone anti-static and corona treatment; ;

performance	empirical approach	unit	Typical values
Weight per unit area	GB/T 451.2-2002	g/m ²	70
thickness	GB/T 3820	μm	200
peeling strength	FZ/T 80007.1-2006	N/2.54cm	1.5
Longitudinal stretching	ASTM D5035	N/2.54cm	180
transverse tensile	ASTM D5035	N/2.54cm	150
Longitudinal elongation	ASTM D5035	%	30
Lateral elongation	ASTM D5035	%	30
longitudinal tear	ASTM D1424	N	5.0
Lateral tearing	ASTM D1424	N	5.0
opaque	GB/T 1543	%	95

Note: These characteristics represent the average value based on the average of each roll, taken uniformly from the entire sheet. Other characteristics are not controlled during the production process, so they will change with the deviation of the 'normal' process.

*This item may vary due to changes in speed, sample size, and fixture T-degree

For more information, please contact the local sales representative or distributor of Yishu Company.

以The above information is based on reliable technical data considered by Yishu Company. The company will revise it based on changes in external knowledge and experience, and Yishu Company does not assume any responsibility or obligation. These information are only for personal use by relevant personnel under specific end use conditions, and the risk of use is borne by them. Due to these terms not being under our control, we make no express or implied warranties, including but not limited to warranties of merchantability and suitability for special purposes, and do not assume any responsibility related to the use of this information.